



Chamber windowsill

Technical Data Sheet

Material	PVC with decorative foil			
Dimensions	Width [mm]	Length [mm]	Height of „nose“ [mm]	Thickness [mm]
	100	6000	40	20
	150			
	200			
	250			
	300			
	350			
	400			
	480			
	250	1500		
		2000		
		2500		
	300	1500		
2000				
3000				
Storage	The product should be stored indoors, out of reach of equipment and in direct sunlight. In conditions that protect the panels from contamination, deformation and mechanical damage.			
Packing	Width [mm]	Length [mm]	Number of pcs. in pack	
	100	6000	2 pcs.	
	150			
	200			
	250			
	300			
	350			
	400			
	480			
	250 cut to size with caps included	1500	1 pc.	
		2000		
		2500		
	300 cut to size with caps included	1500	1 pc.	
2000				
3000				
Tools	Use a fine-toothed saw for cutting.			
Installation temperature	The panels should be left in the room at 20°C for 5h before installation.			
Important installation information	Mount on adhesive - cleaned substrate. Finish the gap between the wall and the sill with silicone.			
Maintenance	Clean with a damp cloth or mild detergent. Do not leave liquid dirt to dry. Intense scrubbing and the use of strong cleaning agents may damage the panel surface or discolour the panel. Do not use solvents or acids or liquids based on these ingredients for cleaning. Do not clean with sharp or rough cloths, sponges or brushes. Do not leave cleaning agents on the surface, rinse thoroughly with water after cleaning, leaving cleaning agents on the surface may cause discolouration.			



Essential characteristics	Performance
Change of linear dimension change after 6h at + 65°C [%]	≤ 0,5
Charpy impact strength [kJ/m ²]	≥ 15
Tensile strength [MPa]	≥ 25
Modulus of elasticity in tension [MPa]	≥ 3300
Film adhesion – peel strength [N/mm]	≥ 2
Vicat softening temperature (in oil) [°C]	≥ 75
Durability – color change after exposure of 590 MJ/m ²	Not more than 3 degree in grey scale



QUICK
INSTALLATION



EASY
INSTALLATION



IMPACT
RESISTANCE



EASY
TO CLEAN

